GrowDex[®]

INSTRUCTIONS FOR USE

CONTENTS

- 1. Introduction

- Introduction
 Safety information
 Product storage instructions
 Practical guidelines and recommendations for starting work with GrowDex*

 A. Practical guidelines and recommendations for starting work with GrowDex
 Recommendations for handling and pipetting GrowDex
 Recommendations when using microplates
 Recommendations when changing media
- 5. Procedures for diluting, mixing and plating GrowDex
- 6. Dilution table7. GrowDex concentrations for a selection of cell-based assays
- 8. Ordering information 9. Contact information

1. INTRODUCTION

GrowDex® has been designed to provide a support matrix for the culture of cells in a wide range of applications. It comprises of two components, nanofibrillar cellulose (NFC) and ultra-pure water. The length of the nanofibrils ranges from 200-300 $\mu m,$ with a diameter in the nanometer scale varying from 5-100 nm. The product

2. SAFETY INFORMATION

In accordance with current regulations (1272/2008 CLP), GrowDex is classified as non-hazardous. The product consists of micro and nanosized cellulose fibrils. The product contains 1.5% cellulose (CAS/EC number 9004-34-6 / 232-674-9) and water (CAS number 732-18-5). The nanofibrillar cellulose is isolated from the Birch tree (Betula sp.). The product is provided sterile.

The product should be handled in accordance with good laboratory (GLP) and safety practices. Use protective gloves and clothes to avoid skin exposure. If exposed wash the skin with water. Use protective laboratory eye wear to avoid contact with the eyes. In its wet state the product does not form dust. If dried however, avoid breathing the dust. Dust filters are recommended. is supplied sterile, ready to use and can be utilized in a variety of cell culture applications, such as 3D spheroid or organoid formation.

GrowDex is for research use only and should not be used for diagnostic or therapeutic purposes.

Description of first aid measures:

- Inhalation: Move to fresh air. Seek medical attention if symptoms appear.
- Skin contact: Rinse with water. Seek medical attention if irritation occurs.
- Eye contact: Rinse with plenty of water for several minutes. Seek medical attention if irritation occurs. • Ingestion: Rinse mouth with plenty of water. If large
- quantities of the product are ingested endeavor to vomit. Seek medical attention if symptoms appear.

NOTE: For further information refer to the GrowDex® Material Safety Data Sheet.

3. PRODUCT STORAGE INSTRUCTIONS

The unopened product has a shelf life of 12 months from date of manufacture and should be stored at $4-22^{\circ}C$ ($39-72^{\circ}F$) and protected from light for optimum performance. Once opened it is recommended that the product is stored undiluted at 4-8°C (39-46°F) for a maximum of 3 months.

If the product has been diluted, e.g. with culture media, then it should be stored at $4-8\,^\circ\text{C}$ (39-46°F) for a maximum of

7 days. If the media contains an unstable component, then storage time will be restricted to the shelf life of the unstable component. Please refer to the manufacturer's guidelines regarding this component.

Do not store the product below 0°C (32°F) as freezing will result in destabilization of the product rendering it unusable.

NOTE: GrowDex is supplied at a working concentration of 1.5%. It is not a concentrate.

4. PRACTICAL GUIDELINES AND RECOMMENDATIONS FOR STARTING WORK WITH GROWDEX

4.1. RECOMMENDATIONS FOR HANDLING AND PIPETTING GROWDEX

a) Low-retention pipette tips should be used to avoid GrowDex sticking to the tip.

4.2. RECOMMENDATIONS WHEN USING MICROPLATES a) Microplates containing GrowDex should be

- A wide bore pipette tip, or one that has been cut, can help with the initial mixing step reducing to a narrower bore tip to increase mixing efficiency. Aspirating and dispensing GrowDex should be performed slowly to avoid air bubbles and to ensure an accurate valuee b)
- c an accurate volume.
- A positive-displacement pipette is useful for pipetting d) viscous materials like undiluted GrowDex. e) For an exact amount of undiluted GrowDex the product
- an also be weighed before dilution.
- Electric dispensing pipettes and automated dispensing systems can be used for dispensing and mixing. f)
- A multi-stepper pipette or automated dispensing system is recommended for repeat dispensing of GrowDex into the well-plates for high throughput applications.
- handled with care. Avoid shaking when moving the plate between locations. b) When culturing adherent cells, the use of low
- attachment micro-plates, or pre-coating with e.g. 0.4% PolyHEMA, is recommended to prevent cells attaching to the bottom of the wells.
- GrowDex is also suitable for high throughput assays in 384 and 1536 well microplates.

4.3. RECOMMENDATIONS WHEN CHANGING MEDIA

- a) When changing the media, extra care should be taken b) When citating the metal, each distribute should be taken not to disturb the top of the gel. It is recommended that the well plate is slightly tilted for easier media change.
 b) If loss of GrowDex occurs, then it is recommended to exchange only half the amount of media at one time.
- The microplate can be centrifuged gently e.g. 100 x g for 5 minutes before changing the media to aid visualization of the hydrogel/media interface.

PROCEDURES FOR DILUTING, MIXING AND PLATING 5. GROWDEX

The stiffness of GrowDex can be adjusted by diluting the product with e.g. cell culture media, PBS, or ultra-pure water. GrowDex concentrations of 0.2 - 1.0% are commonly used for cell culture applications. The optimal concentration will depend on the cell type being used, refer to Section 7 and the GrowDex application notes for examples and recommended assay setup details.

> ϵ Continues

NOTE: GrowDex is supplied at a concentration of 1.5%, this means the product contains 1.5% cellulose and 98.5% ultra-pure water. It is not a concentrate




Image 1. Diluting, mixing and plating GrowDex

Diluting GrowDex

- Pipette the required amount of diluent/media, without a) cells, into a test tube. **NOTE:** If embedding cells inside GrowDex consider the volume of the cell suspension that will be added later to ensure the correct final volume and concentration is achieved.
- b) Before opening the syringe cap move the plunger gently back and forth to release it before dispensing. Dispense GrowDex directly from the syringe into the test tube containing the diluent. Graduations on the syringe indicate the volume dispensed or alternatively FrowDex may be weighed (1 ml = 1 g).

EXAMPLE 1: Cells embedded in GrowDex

Working concentration required = 0.5% Final volume = 1 ml

- a) Pipette 567 µl culture medium into a test tube. b) Add 333 µl GrowDex and mix by pipetting up and down until the solution is homogenous by visual inspection. (Refer to Section 5 – Procedures for diluting, mixing and plating GrowDex). Low-retention pipette tips are recommended for this procedure (Refer to Section 4 - Practical guidelines and recommendations for starting work with GrowDex). c) Add 100 µl cell suspension to the diluted GrowDex
- slowly and stir carefully using the pipette tip to evenly disperse the cells.
- d) Transfer 100 μl of diluted GrowDex with cells to the 96 well plate.
- e) Add 100 µl of culture medium carefully on top not to disturb the GrowDex layer.
 f) Incubate at 37°C.

- c) Mix GrowDex and diluent by first swirling the pipette Mix GrowDex and diluent by first swirling the pipette tip along the wall of the tube and then by pipetting up and down for a minimum of 90 seconds. A wide bore pipette tip or one that has been cut can help with the initial mixing step. Continue until a homogenous solution is achieved by visual inspection. Increase the speed of pipetting towards the end of mixing and make sure the budged flow: smoothly through the pipetter tip.
- the hydrogel flows smoothly through the pipette tip. d) Avoid air bubble formation by keeping the pipette tip submerged in the solution throughout the mixing process.

EXAMPLE 2: Cells seeded on top of GrowDex Working concentration required = 0.45% Final volume = 2 ml

- a) Pipette 1400 µl culture medium into a test tube. b) Add 600 µl GrowDex and mix by pipetting up and down until the solution is homogenous by visual inspection. (Refer to Section 5 – Procedures for diluting, mixing and plating GrowDex). Low-retention pipethe tips are recommended for this procedure (Refer to Section 4 - Practical guidelines and recommendations for starting work with GrowDex). c) Transfer 100 μl of diluted GrowDex to the 96 well
- plate.
- d) Add cells in 100 µl culture medium carefully on top of the GrowDex layer.
 e) Incubate at 37°C.

6. DILUTION TABLE

Volume of GrowDex diluent, and cell suspension required for preparation of GrowDex dilution for a variety of final working concentrations.

| FINAL GROWDEX CONCENTRATION | VOLUME OF GROWDEX STOCK SOLUTION (1.5 %) | VOLUME OF DILUENT | VOLUME OF CELL SUSPENSION | TOTAL VOLUME |
|--------------------------------|--|----------------------|------------------------------|-----------------|
| 1.0 % | 800 µl | 300 µl | 100 µl | 1200 µl |
| 0.8 % | 600 µl | 425 µl | 100 µl | 1125 µl |
| 0.5 % | 400 µl | 700 µl | 100 µl | 1200 µl |
| 0.2 % | 200 µl | 1200 µl | 100 µl | 1500 µl |

Please note: 'Cells seeded on top of GrowDex' procedure, add the cell suspension volume to diluent volume. Example: 0.5 % final GrowDex concentration and total volume of 1.2 ml, 400 ul of GrowDex stock + 800 ul media with cells.

7. **GROWDEX CONCENTRATIONS FOR A SELECTION OF CELL-BASED ASSAYS**

| NEURONAL CELLS | | | |
|--------------------------------------|---------------|----------------------|--|
| CELL LINE | GROWDEX CONCN | CELL SEEDING DENSITY | |
| iPSC derived neural progenitor cells | 1.0 % | 500 cells / µl | |
| hESC derived neuronal cells | 1.0 % | 5000 cells / µl | |

| STEM CELLS | |
|---------------|---------------------------------|
| GROWDEX CONCN | CELL SEEDING DENSITY |
| 0.2 % | 1000 cells / µl |
| 0.5 % | 2000 cells / µl |
| 0.5 % | 5 x higher than in 2D |
| | GROWDEX CONCN 0.2 % 0.5 % |

| | CANCER CELLS | |
|---------------------------------|---------------|----------------------|
| CELL LINE | GROWDEX CONCN | CELL SEEDING DENSITY |
| U251, glioblastoma | 0.2 % | 1000 cells / µl |
| HepG2, hepatocellular carcinoma | 0.3 % | 50 cells / µl |
| MCF7, breast adenocarcinoma | 0.37 % | 250 cells / µl |
| BT474, breast cancer | 0.4 % | 80 cells / μl |
| OVCAR8, ovarian cancer | 0.8 % | 100 cells / µl |

| | HEPATIC CELLS | HEPATIC CELLS | |
|---------------------|---------------|----------------------|--|
| CELL LINE | GROWDEX CONCN | CELL SEEDING DENSITY | |
| HepaRG | 1.0 % | 1000 cells / µl | |
| Primary hepatocytes | 0.5 % | 1000 cells / µl | |

8. ORDERING INFORMATION

| CATALOGUE CODE | DESCRIPTION | QUANTITY (ml) |
|----------------|-------------------------------|---------------|
| 100 103 002 | GrowDex | 2.5 |
| 100 103 005 | GrowDex | 5.0 |
| 100 103 010 | GrowDex | 10.0 |
| 100 103 305 | GrowDex multipack | 3 × 5.0 |
| 100 103 905 | GrowDex + GrowDase combo pack | 5.0 + 2.5 |
| 900 102 002 | GrowDase enzyme | 2.5 |

Contact us at **biomedicals.sales@upm.com** for a quotation or to place an order.

CONTACT INFORMATION 9.

Additional information on all products and applications can be found on our website **www.growdex.com**

- EMAIL:
- UPM-Kymmene Corporation /Biomedicals Alvar Aallon katu 1 P.O. Box 380 00101 Helsinki Finland POST:
- +358 (0)204 15 110 FAX:

